

CORNING

Corning® HI 1060 FLEX & RC HI 1060 FLEX Specialty Optical Fibers

High Index / Bend Insensitive



High performance WDM components and ultra-low bend loss applications

Manufactured with our patented outside vapor deposition (OVD) process, Corning® HI 1060 FLEX specialty fiber sets the worldwide standard for uniformity and reliability. Completely re-engineered for fused biconic taper component manufacturing, this specialty fiber is ideal for use in smaller footprint components and EDFAs. Combining ultra-low bending loss, low insertion loss, and excellent spliceability, Corning HI 1060 FLEX specialty fiber enables higher yields and performance throughout the value chain.

Applications

- Pigtails for bend-insensitive applications
- Premium-grade WDM couplers for EDFAs
- Tao couplers
- Splitters and combiners
- CATV couplers
- Ultra-compact components requiring small bend radii
- Low loss fused devices for C-Band and L-Band

Features

- Outstanding consistency and uniformity using our patented Outside Vapor Deposition (OVD) process
- Dual acrylate coating system provides excellent protection from microend-induced attenuation and superior mechanical robustness
- Ultra-low bending loss
- Low excess loss
- Low splice loss to Corning® SMF-28e+® fiber and Corning® ER 1550C3
- Excellent geometry control
- RC HI 1060 FLEX offers 80 µm diameter for subminiature packaging

Key Optical Specifications	HI 1060 FLEX and RC HI 1060 FLEX
Operating Wavelength (nm)	> 980
Fiber Cutoff Wavelength (nm)	930 ± 40
Maximum Attenuation (dB/km)	≤ 2.5 @ 980 nm ≤ 1.0 @ 1550 nm
Mode-Field Diameter (μm)	4.0 ± 0.3 @ 980 nm 6.3 ± 0.3 @ 1550 nm

Key Geometric, Mechanical, and Environmental Specifications	HI 1060 FLEX	RC HI 1060 FLEX
Cladding Outside Diameter (μm)	125 ± 0.5	80 ± 1
Coating Outside Diameter (μm)	245 ± 10	165 ± 10
Core-to-Cladding Concentricity (μm)	≤ 0.3	≤ 0.5
Standard Lengths	500 m, 1 km, 2 km, 5 km, 10 km	
Proof Test (kpsi)	100 or 200	
Operating Temperature (°C)	-60 to +85	

Performance Characterizations*	HI 1060 FLEX and RC HI 1060 FLEX
Nominal Delta (%)	1.06
Numerical Aperture	0.21
Refractive Index Value – Core	1.468 @ 850 nm
Core Diameter (μm)	3.4
Dispersion (ps/nm/km)	-65 @ 980 nm -50 @ 1060 nm

*Values in this table are nominal or calculated values

Typical Splice	HI 1060 FLEX	Corning® SMF-28e+®	RC SMF	ER 1550C3	HI 1060	HI 980	PM 980
Wavelength (nm)	1550	1550	1550	1550	980	980	980
HI 1060 FLEX (dB)	0.03	0.07	–	0.03	0.06	0.04	0.09
RC HI 1060 FLEX (dB)	–	0.22	0.12	0.08	–	–	–

For more information about Corning's leadership in specialty fiber technology, visit our website at corning.com/specialtyfiber. To obtain additional technical information, an engineering sample, or to place an order for this product, please contact us at:

Tel: +1-607-974-9974

Fax: +1-607-974-4122

E-mail: specialtyfiber@corning.com



Corning Optical Communications LLC • 4200 Corning Place • Charlotte, NC 28216 USA
800-743-2675 • FAX: 828-325-5060 • International: +1-828-901-5000 • www.corning.com/opcomm

Corning Optical Communications reserves the right to improve, enhance, and modify the features and specifications of Corning Optical Communications products without prior notification. A complete listing of the trademarks of Corning Optical Communications is available at www.corning.com/opcomm/trademarks. All other trademarks are the properties of their respective owners. Corning Optical Communications is ISO 9001 certified. © 2020 Corning Optical Communications. All rights reserved. OEM-077-AEN / November 2020